



Harzverbrauchstabelle Hausanschlussliner

Linertyp	Spalt in [mm]	Harzbedarf in kg/lfm [kg]									
		50	63	70	80	100	125	150	200	250	300
ThermoLiner plus	10					1,40	1,65	2,20	2,75	3,65	4,41
ThermoLiner 3,5	7					1,02	1,15	1,50	1,90	2,50	3,00
ThermoLiner 5,0	10							2,25	2,88	3,76	4,55
ThermoLiner Steam PP	11					1,45	1,70	2,20	3,10	3,65	4,40
Bendiliner	7	0,50	0,65	0,65	0,85	1,05	1,25	1,57	2,00	3,65	
ThermoLiner Stretch	10					1,50	1,80	2,25	2,88		
ThermoLiner S	10					1,45	1,65	2,20	2,70	3,55	4,30
Softliner	7			0,70	0,80	1,00	1,20	1,50	1,90	2,50	3,00

Harzverbrauchstabelle Hausanschlussliner / Resin consumption for lateral liners

Status: Mai 2017